



Weberfloor print

Colour Hardener for
Stamped Concrete

Flooring

PRODUCT

Coloured mortar that is applied on fresh concrete and allows its stamping and colouring, providing an attractive and resistant rolling layer

SCOPE OF USE

- For dwellings, housing developments, leisure areas, public spaces, shopping centres, parks, car parks, historic environments, pavements...

Types of finish:

- Cobblestone, flagstone, slate, brick, pebblestone, wood...

ADVANTAGES

- High mechanical strength
- Spray application on fresh concrete
- Easy smoothing on the concrete
- Highly decorative finishes
- Range of 15 colours

APPLICABLE STANDARDS

EN 12808-2

INSTRUCTIONS FOR USE

SUBSTRATE PREPARATION

- Once the base is compacted and smooth to receive the concrete, lay a reinforcement mesh.
- Prepare the formwork. Its height should not exceed the thickness of the concrete slab.

TECHNICAL SPECIFICATIONS

Colour

Range of 5+ colours

Coverage

4 -4.5kg/m² (in two coats)

Compression Strength

>25 MPa

Abrasion resistance according to UNE-EN 12808-2:

190 mm³

Flexural strength

> 4 MPa

RECOMMENDATIONS FOR USE

Application of weberfloor print by means of spraying directly onto the still plastic concrete.

- Do not apply with excessive water on the concrete surface.
- Apply in two coats to assure full coverage.
- weberfloor print should be fully integrated into the concrete slab.
- Concrete slab thickness: 7 - 10 cm approx

PRODUCT APPLICATION

- Spread the concrete evenly. Smooth the fresh concrete surface with a magnesium float to open the pores.
- Spray on weberfloor print by hand (4 kg/m² approximately, in two coats), making sure that the concrete is fully covered.
- Smooth the whole surface with a float until the colour is fully integrated into the concrete.
- For the stamping process, spray on a coat of weber DM and print with the moulds selected. Then weber SL should be applied to cure and seal the concrete

PRECAUTIONS

- Temperature for use, between 5°C - 35°C
- Do not add water to the product once it has been sprayed onto the concrete.

STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

SAFETY PRECAUTIONS

The product irritates the eyes, airways and skin. Wear goggles with lateral protection, dust mask in areas with limited ventilation, proper work clothing and protective gloves. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Ghana. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.